



EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar
İstanbul/ TÜRKİYE



TEST REPORT
DENEY RAPORU

EKOTEKS

AB-0583-T

24022474

10-24

Customer name:

Address:

Buyer name

Contact Person:

Order No:

Article No:

Name and identity of test item:

PALA SUNİ DERİCİLİK SAN VE TİC LTD ŞTİ.
YENİDOĞAN MAH ABDİ İPEKÇİ CAD ÇİZMECİ İŞ MERKEZİ NO:87
İÇ KAPI NO:4 BAYRAMPAŞA İSTANBUL

-

-

-

URLA

One sample of beige artificial leather panel.

The date of receipt of test item:

16.09.2024

Re-submitted/re-confirmation date:

-

Date of test:

16.09.2024-11.10.2024

Remarks:

-

Sampling:

The results given in this report belong to the received sample by vendor.

End-Use:

-

Care Label:

-

Number of pages of the report:

3

The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the Mutual recognition of test reports. EKOTEKS LABORATUVAR ve GÖZETİM HİZMETLERİ A.Ş. accredited by TÜRKAK under registration number [AB-0583-T] for ISO 17025:2017 as test laboratory.

The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test methods are given on the following pages which are part of this report. ()



Date
11.10.2024

Customer Representative
Zahide TAPAN

Head of Testing Laboratory
Sevim A. RAZAK

This report shall not be reproduced other than in full except with the permission of the laboratory. Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T

24022474

10-24

REQUIRED TESTS	EVALUATION	COMMENTS
PHYSICAL PROPERTIES TESTS		
Abrasion ⁽¹⁾	-	
⁽¹⁾ No requirement was given		

REMARK: Original samples are kept for 3 months and all technical records are kept for 5 years unless otherwise specified. If requested, measurement uncertainty will be reported. But unless otherwise specified, measurement uncertainty is not considered while stating compliance with specification or limit values. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor $k=2$, providing a level of confidence of approximately 95 %. The declaration of conformity was given in accordance with the Simple Acceptance Decision Rule. (without considering the level of confidence and measurement uncertainty, evaluation of suitability or non-conformity based on whether the test result obtained is only within the specified limits) Tests marked (*) in this report are not included in the accreditation schedule.



This report shall not be reproduced other than in full except with the permission of the laboratory.
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM
HİZMETLERİ A.Ş.**

AB-0583-T

24022474

10-24

TEST RESULTS

DETERMINATION OF THE ABRASION RESISTANCE OF FABRICS BY THE MARTINDALE METHOD-DETERMINATION OF SPECIMEN BREAKDOWN :
ISO 12947-2:2016 /

Martindale Test Machine (47.5±2 rpm) with Lissajous Figure.

12 kPa pressure, (795±7) g mass./

Performed in the conditioned room (20±2°C-65%±4).

Criteria for the end point in the evaluation are given in the table below.

Fabric Type :	Panel	RESULT	REQUIREMENT
Sample 1		No Abrasion @ 100.000 revs	-
Sample 2		No Abrasion @ 100.000 revs	
Sample 3		No Abrasion @ 100.000 revs	
Overall Result **		No Abrasion @ 100.000 revs	

****The overall result is the lowest individual test result of all the test specimens tested.**

Note: The Endpoint Criterion was performed according to the customer's request.

Fabric Type	END-POINT CRITERIA ^a	
	“Thread breakage” Criteria:	Worn off area” Criteria
Woven Fabric (without pile)	Two threads completely broken	NA

^a : Alternative test specimen breakdown point criteria could be used as agreed between the interested parties and should be reported.

^b

N.A : Not Applicable