



**EKOTEKS**

**TÜRKAK**  
**TÜRK AKREDİTASYON KURUMU**  
**TURKISH ACCREDITATION AGENCY**  
tarafından akredite edilmiş



Test  
TS EN ISO/IEC 17025  
AB-0583-T

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**  
Esenyurt Firuzköy Bulvarı No:29 34325 Avcılar  
İstanbul/ TÜRKİYE

**TEST REPORT**  
*DENEY RAPORU*

AB-0583-T

17030616-  
ing-Add

09-21

**Customer name:** SALDER SUNİ DERİ TEKSTİL SAN. A.Ş.  
**Address:** Hayrabolu Organize Sanayi Bölgesi Çelik Sok. No:6 HAYRABOLU/  
TEKİRDAĞ  
**Buyer name:** -  
**Contact Person:** OKMEN MENEKŞE  
**Order No:** -  
**Article No:** TOSCANO  
**Name and identity of test item:** One sample of back face cream knitted fabric coated, ecru artificial leather  
panel  
**The date of receipt of test item:** 01.08.2021  
**Re-submitted/re-confirmation  
date:** 16.08.2021  
**Date of test:** 16.08.2021-27.09.2021  
**Remarks:** -  
**Sampling:** The results given in this report belong to the received sample by vendor.  
**End-Use:** -  
**Care Label:** Not specified.  
**Number of pages of the report:** 6

*The Turkish Accreditation Agency (TURKAK) is signatory to the multilateral agreements of the European  
co-operation for the Accreditation (EA) and of the International Laboratory Accreditation (ILAC) for the  
Mutual recognition of test reports.*

*The test and/or measurement results, the uncertainties (if applicable) with confidence probability and test  
methods are given on the following pages which are part of this report.*

**Seal**

**Date**  
27.09.2021

**Customer Representative**  
Özlem ULUS

**Head of Testing Laboratory**  
Sevim A. RAZAK

This report shall not be reproduced other than in full except with the permission of the laboratory.  
Testing reports without signature and seal are not valid.

**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

17030616-  
ing-Add

09-21

## TEST RESULTS

### TENSILE STRENGTH; TS EN ISO 1421:2017 METHOD 1

Instron 5969 (Load: 50 kN), Strip Method.

Speed: 100 mm/dk±10 mm/min, Gauge length: 200 mm±1 mm

Pre-load was not applied.

The average results are given for weft and warp direction of 3 samples.

Performed in the conditioned room (20±2°C-65%±4).

	<u>RESULT</u>	<u>REQUIREMENT</u>
Weft	387.2 N	-
Warp	459.1 N	-

### TEAR STRENGTH; TS EN ISO 4674-1:2006

Method A (Double Tear)/Pre-treatment was not applied.

Instron 5969. Speed:100±10 mm/min, Gauge length:100±1 mm

The average results are given for weft and warp direction of 2 samples.

Performed in the conditioned room. (20±2°C - 65% ±4)

	<u>RESULT</u>	<u>REQUIREMENT</u>
Weft	72.5 N	-
Warp	48.7 N	-

### SEAM STRENGTH; TS EN ISO 13935-2: 12014(\*)

INSTRON 5969 Speed: 50 mm/min, Gauge Length: 100 mm±1 mm

Seam density: 100 mm@50±2 seam.

Performed in the conditioned room (20±2°C-65%±4).

	<u>RESULT</u>	<u>FAILURE</u>	<u>REQUIREMENT</u>
Weft	210.6 N	FTS	-
Warp	350.4N	FTJ	-

FTS: Fabric tear at seam

FTJ: Çenede kumaş yırtılması.



**EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.**

AB-0583-T

17030616-  
ing-Add

09-21

## TEST RESULTS

### FLAMMABILITY; IMO Resolution A.652(16): 1989 – Smouldering Cigarette Test

Original samples were tested

#### Conditioning

**Prior to testing:** The sample was conditioned before the test for at least 16 hours in an atmosphere having a temperature of 20±5 °C and a relative humidity of 50±20 %

**Test Condition :** The sample was tested in an atmosphere with a temperature of 15°C to 30°C and relative humidity of 20% to 70 %.

#### Filling Specification

**Filling Type** : Non fire retardant polyurethane foam  
**Size** : 450 x 300 x 75 mm (back) & 450 x 150 x 75 mm (seat)  
**Density / Hardness** : 20-22 kg/m<sup>3</sup> / Type B, 130 N

**Specimen size** : 800 x 650 mm (length x width)

**Ignition Source** : Calibrated Senior Service Virginia cigarette

“The following test results relate only to the ignitability of the combination of materials under the particular conditions of test ; they are not intended as a means of assessing the full potential fire hazard of the materials in use.”

Criteria Of Failure	Test 1	Test 2
<b>Progressive smouldering failure</b>		
Progressive smouldering of the interior and/or cover is observed at any time within a period of 1 hour of the placement of the cigarette	NO	NO
<b>Flaming Failure</b>		
Any flaming of the interior and/or cover is observed at any time within a period of 1 hour of the placement of the cigarette	NO	NO
On final examination whether progressive smouldering should be observed when dismantle assembly and examine internally	NO	NO
<b>RESULT</b>	<b>PASS</b>	

O : Observed  
NO : Not observed

EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.

AB-0583-T
17030616- ing-Add
09-21

**Test Details**

	<b>Test 1</b>	<b>Test 2</b>
Smoking ceased time (after placement of the cigarette) (min:sec)	02:21	02:28
Flame ceased time (min:sec)	-	-
Progressive smouldering time (min:sec)	-	-
Melting	NO	NO
Dripping	NO	NO
Charring	O	O

“The fabric tested meets the requirements of IMO Resolution A.652(16): 1989 (The smouldering cigarette test) ”

EKOTEKS LABORATUVAR ve GÖZETİM  
HİZMETLERİ A.Ş.

AB-0583-T
17030616- ing-Add
09-21

## TEST RESULTS

DETERMINATION OF ANTIFUNGAL ACTIVITY: AATCC 30:2013 (Test III- Agar Plate)

Zone of inhibition (mm) <sup>(1)</sup>	Growth of microorganisms <sup>(2)</sup>	Result
Was not observed	Was not observed	Effective

<sup>(1)</sup> Inhibition area around the width of clear zone surrounding test specimen (mm)

<sup>(2)</sup> Growth microorganisms on the fabric / not observed

Microorganism	<i>Aspergillus niger</i> ( ATCC 6275 )
Incubation conditions	28±1°C
Incubation periods	7 days
Diameter of test specimens	3.8 cm
Culture medium	Sabouraud 4 % Glucose Agar